


Fully Vitrified Dust Pressed Tiles - Annex G, Group Bla



STEEL GREY LRV 35
148 x 148 DW-PHSGR1515



DARK GREY LRV 16
148 x 148 DW-PHDGR1515




QUARTZ LRV 37
148 x 148 DW-PHQUZ1515



STONE LRV 46
148 x 148 DW-PHSTO1515



WHITE LRV 52
148 x 148 DW-PHWHT1515



BLACK LRV 9
148 x 148 DW-PHBLK1515



RED LRV 12
148 x 148 DW-PHRED1515



SURFACE DETAIL

Features / Suitability

148 x 148 x 9mm • 44pcs / 20kg per m²

Another general purpose slip resistant tile suitable for wet and dry areas, shod and barefoot, inside and out. The pinhead profile has good volume displacement properties (V4) and this attractive profile is also comfortable for bare feet making it a great choice for spa/leisure environments. Other applications include:

- ▶ Most internal and external applications, wet and dry, included ramped areas
- ▶ Light industrial areas
- ▶ Showrooms, waiting and reception areas
- ▶ Hospitality establishments, both front of house and food preparation areas
- ▶ Commercial and retail
- ▶ Dry-wet spaces such as swimming pool changing rooms, showers
- ▶ Public toilets and washrooms

DISPLACEMENT VOLUME	SHOD DRY (4S96 dry)	SHOD WET (4S96 wet)	BAREFOOT WET (TRRL 55 wet)	RAMP TEST
V4	62	54	48	R11 C



FULL TECHNICAL
SPECIFICATIONS
OVERLEAF

Fully Vitrified Dust Pressed Tiles - Annex G, Group Bla

	Standard	Requirement (148 x 148 x 9mm)	Typical Test Value
Length & Width	EN ISO 10545-2	+/- 0.9 mm	Conforms
Thickness	EN ISO 10545-2	+/- 0.5 mm	Conforms
Straightness of Sides	EN ISO 10545-2	+/- 0.75 mm	Conforms
Rectangularity	EN ISO 10545-2	+/- 0.75 mm	Conforms
Surface Flatness: A-B-C	EN ISO 10545-2	+/- 0.75 mm	Conforms
Surface Quality	EN ISO 10545-2	A minimum of 95% of the tiles will be free from visible defects	Conforms
Water Absorption % by Mass	EN ISO 10545-3	< 0.5%	Group Bla Fully Vitrified
Breaking Strength $\geq 7.5\text{mm}$	EN ISO 10545-4	>1300N	Conforms 3583N
Modulus of Rupture	EN ISO 10545-4 N/mm ² N	Minimum 35 N/mm ² Individual minimum 32	Conforms
Resistant to Deep Abrasion of Unglazed Tiles	EN ISO 10545-6	Maximum 175vmm ³	Between 19.5mm / 62vmm ³ and 22.5mm / 94vmm ³
Thermal Shock Resistance	EN ISO 10545-9	Cycled 10 times between temperature of 15° & 145° C	Fully Resistant
Frost Resistance	EN ISO 10545-12	100 Freeze Thaw Cycles	No Damage
Resistance to Household Chemicals and Swimming Pool Salts	EN ISO 10545-13	Minimum UB	UA No Visible Effects
	EN ISO 10545-13	Low Acids & Alkali	ULA No Visible Effects
	EN ISO 10545-13	High Acids & Alkali	UHA No Visible Effects
Surface Hardness MOHS UNE 67-101-92-2012	>6	>6	>6
Reaction to Fire EN14411 Annex ZA, classified without testing (CWT)	93/68/EEC	When installed on walls A1 When installed on floors A1 _{FL}	Non combustible
Recycled Content	Pre Consumer 4%		Post Consumer 100%
Environmental	Products do not contain VOCs		

Architects, specifiers and design professionals:

For further information, advice or guidance on choosing specific Dorset Woolliscroft products please contact us on 01392 473030 / info@dorsetwoolliscroft.com